



RS
Motorbike
Paint
LTD

SPECIALISTS IN ORIGINAL MOTORBIKE COLOURS

RS Motorbike Paint Limited
Unit 5 Alpha Business Park, Welham Green,
Hertfordshire AL9 7NT
Tel / Fax: 01707 273219
Web: www.rsbikepaint.co.uk
Email: sales@rsbikepaint.co.uk
(VAT Reg. No. 364 1483 53)

COB/Polyurethane Transparent Candy Color “Dye/Ink”

Description

Transparent color to apply over base paint color. Must be followed with clearcoat lacquer.

Mixing Ratio

Your candy paint will need to be mixed with polyurethane thinner/reducer at a ratio of 50% ie 2 parts paint to 1 part thinner/reducer. We are unable to supply this due to dangerous goods shipping restrictions, however you should be able to source this locally.

Application

Spray viscosity at 20 °C: 14”-15” DIN 4; HS CYCLE: 20-22” DIN4

Air cap: 1.2-1.5 mm

Air pressure: 45-50psi

N° of coats: 2 - 3 (approximately)

Please note the number of coats will affect the final color thus comparison should be made with the original paintwork. Do not apply a thick film. Color will darken with more coats. Always do a test first. Use of the correct base is vital.

Drying Times

Allow 15 minutes between coats. Allow to dry for 30 minutes in a dust free area. Apply clearcoat lacquer.