



Aerosol and Touch up Matt/Satin Clearcoat

Description

Two component acrylic clearcoat which can be applied over most suitably prepared basepaints. Any gloss surfaces must be lightly rubbed down with 1200 sand paper before application. Easy application, fast drying, non yellowing.

Drying Times (air drying at 20°C)

Number of coats: 2 – 3

Dust free 3 – 5 mins

Tack free 15-20 mins

Through drying: 6 hours

Interval between coats: 10 mins

The complete hardening occurs in the following 3-4 days.

OBSERVATIONS

The painted substrate must not be exposed to severe conditions in the first days after the painting. Until the film has reached the complete cross-linking, strong humidity condensations, like dew and frost and contact with aggressive agents like smog, detergents, salt on the roads, must be avoided.